

# Standard Vietnamese Rubber (SVR)

## Natural Rubber Comparison Chart

Parameter	Unit	SVR CV50	SVR CV60	SVR L	SVR 3L	SVR 5	SVR 10	SVR 20
Dirt (max)	% wt	0.03	0.03	0.02	0.03	0.05	0.08	0.16
Ash (max)	% wt	0.50	0.50	0.50	0.50	0.50	0.75	1.00
Nitrogen (max)	% wt	0.60	0.60	0.60	0.60	0.60	0.60	0.60
Volatile Matter (max)	% wt	0.80	0.80	0.80	0.80	0.80	0.80	0.80
Po		NA	NA	35	35	30	30	30
PRI		60	60	60	60	60	50	40
Colour Lovibond Scale (individual value, max)		NA	NA	4.0	6.0	NA	NA	NA
Mooney Viscosity** (ML, 1+4, 100°C)		50 +/- 5	60 +/- 5	NA	NA	NA	NA	NA

These figures are limits, not typical values. Typical values will vary by producer.